

CERTIFICATE OF MAILING

I hereby certify that this correspondence is being deposited with the United States Postal Service as First Class Mail in an envelope addressed to:

Assistant Commissioner for Patents
Washington, D.C. 20231

on October 1, 2001

RIMMA MITELMAN
Reg. No. 34,396
Attorney for Applicant(s)

10/01/01

Date of
Signature

PATENT

#Y2-0340-UNI

Case #C2068(C)

1700

1751

#5

flw

IN THE UNITED STATES PATENT AND TRADEMARK OFFICE

Applicant: Kumar et al.

Serial No.: 09/852,095

Filed: May 9, 2001

For: SOIL RELEASE POLYMERS AND LAUNDRY DETERGENT COMPOSITIONS
CONTAINING THEM

Edgewater, New Jersey 07020

October 1, 2001

SUBMISSION OF PRIORITY DOCUMENT

OCT 10 2001

TC 1700

Assistant Commissioner for Patents
Washington, D.C. 20231

Sir:

Pursuant to rule 55(b) of the Rules of Practice in Patent Cases, Applicant(s) is/are submitting herewith a certified copy of the Indian Application No. 423/MUM/00 filed May 9, 2000, and the United Kingdom Application No. 0018287.3 filed July 25, 2000, upon which the claim for priority under 35 U.S.C. § 119 was made in the United States.

It is respectfully requested that the priority document be made part of the file history.

Respectfully submitted,

Rimma Mitelman

Rimma Mitelman
Registration No. 34,396
Attorney for Applicant(s)

RM/mt
(201) 840-2671



INVESTOR IN PEOPLE


The Patent Office
Concept House
Cardiff Road
Newport
South Wales
NP10 8QQ

I, the undersigned, being an officer duly authorised in accordance with Section 74(1) and (4) of the Deregulation & Contracting Out Act 1994, to sign and issue certificates on behalf of the Comptroller-General, hereby certify that annexed hereto is a true copy of the documents as originally filed in connection with the patent application identified therein.

In accordance with the Patents (Companies Re-registration) Rules 1982, if a company named in this certificate and any accompanying documents has re-registered under the Companies Act 1980 with the same name as that with which it was registered immediately before re-registration save for the substitution as, or inclusion as, the last part of the name of the words "public limited company" or their equivalents in Welsh, references to the name of the company in this certificate and any accompanying documents shall be treated as references to the name with which it is so re-registered.

In accordance with the rules, the words "public limited company" may be replaced by p.l.c., plc, P.L.C. or PLC.

Re-registration under the Companies Act does not constitute a new legal entity but merely subjects the company to certain additional company law rules.



Signed *Andrew Gersey*
Dated 28 March 2001



Request for grant of a patent

(See the notes on the back of this form. You can also get an explanatory leaflet from the Patent Office to help you fill in this form)

1. Your reference

C2068(C)/PMK

0018287.3

2. *(The Patent Office will fill in this part)*

25 JUL 2000

3. Full name, address and postcode of the or of each applicant (*underline all surnames*)

UNILEVER PLC
UNILEVER HOUSE, BLACKFRIARS
LONDON, EC4P 4BQ

Patents ADP number (*if you know it*)

1628002

If the applicant is a corporate body, give the country/state of its incorporation

UNITED KINGDOM

4. Title of the invention

**SOIL RELEASE POLYMERS AND LAUNDRY
DETERGENT COMPOSITIONS CONTAINING
THEM**

5. Name of your agent (*if you have one*)

FRANSELLA, Mary Evelyn

"Address for Service" in the United Kingdom to which all correspondence should be sent (*including the postcode*)

**PATENT DEPARTMENT, UNILEVER PLC
COLWORTH HOUSE, SHARNBROOK
BEDFORD, MK44 1LQ**

Patents ADP number (*if you know it*)

6893440001

6. If you are declaring priority from one or more earlier patent applications, give the country and the date of filing of the or of each of these earlier applications and (*if you know it*) the or each application number

Country	Priority application number (<i>if you know it</i>)	Date of filing (day / month / year)
INDIA	423/MUM/00	09 MAY 2000

7. If this application is divided or otherwise derived from an earlier UK application, give the number and the filing date of the earlier application

Number of earlier application	Date of filing (day/month/year)

8. Is a statement of inventorship and of right to grant of a patent required in support of this request? *Answer 'Yes' if:*

YES

- a) any applicant named in part 3 is not an inventor, or
 - b) there is an inventor who is not named as an applicant, or
 - c) any named applicant is a corporate body.
- See note (d))

9. Enter the number of sheets for any of the following items you are filing with this form. Do not count copies of the same document

Continuation sheets of this form

Description	22
Claim(s)	6
Abstract	1
Drawing(s)	12 <i>X 12 M.</i>

10. If you are also filing any of the following, state how many against each item.

Priority Documents

Translations of priority documents

Statement of inventorship and right to grant of a patent (*Patents Form 7/77*)

Request for preliminary examination and search (*Patents Form 9/77*)

1 *A*

Request for substantive examination (*Patents Form 10/77*)

Any other documents
(please specify)

11.

I/We request the grant of a patent on the basis of this application.

Signature(s)

Rajan

Date: 25/07/00

Dilshad RAJAN, Authorised Signatory

12. Name and daytime telephone number of person to contact in the United Kingdom

Petra Kimber, Tel 01234 222893

Warning

After an application for a patent has been filed, the Comptroller of the Patent Office will consider whether publication or communication of the invention should be prohibited or restricted under Section 22 of the Patents Act 1977. You will be informed if it is necessary to prohibit or restrict your invention in this way. Furthermore, if you live in the United Kingdom, Section 23 of the Patents Act 1977 stops you from applying for a patent abroad without first getting written permission from the Patent Office unless an application has been filed at least 6 weeks beforehand in the United Kingdom for a patent for the same invention and either no direction prohibiting publication or communication has been given, or any such direction has been revoked.

Notes

- If you need help to fill in this form or you have any questions, please contact the Patent Office on 0645 500505.
- Write your answers in capital letters using black ink or you may type them.
- If there is not enough space for all the relevant details on any part of this form, please continue on a separate sheet of paper and write "see continuation sheet" in the relevant part(s). Any continuation sheet should be attached to this form.
- If you have answered 'Yes' Patents Form 7/77 will need to be filed.
- Once you have filled in the form you must remember to sign and date it.
- For details of the fee and ways to pay please contact the Patent Office.

SOIL RELEASE POLYMERS AND LAUNDRY DETERGENT
COMPOSITIONS CONTAINING THEM

5

TECHNICAL FIELD:

The present invention relates to novel soil release polymers for detergent formulations capable of enhancing soil removal
10 from cotton or polyester fabric or their blends and a process for the preparation of the same.

BACKGROUND OF THE INVENTION:

15

The washing of soiled fabrics with a laundry detergent is essentially a two step process. In the first stage, the detergent must remove the soil particles from the fabric and suspend them in the soil solution. In the second stage the
20 detergent must prevent soil particles and other insolubles from re-depositing on the cloth before and after the fabric is removed from the soil solution or the rinse solution. Polymers are known to aid both processes - soil release polymers enhance soil removal from the fabric whilst anti-redeposition polymers prevent the deterged soil from
25 depositing on the fabric.

The thrust in recent times has been the development of soil release polymers (SRPs), which can be incorporated into
30 detergent formulations, to enhance the removal of soil from the fabric. SRPs adsorb on the fabric surface, modifying

properties like the hydrophilic or hydrophobic nature of the fabric and its surface energy. Consequent soil removal is greater than what is possible with a conventional detergent formulation.

5

Soil release polymers disclosed in the literature address the problem of removal of oily or fatty soils from polyester. Polyester is a hydrophobic fabric and removal of hydrophobic, oily soils from the fabric has historically been a problem.

10 The problem has been circumvented in part by using soil release polymers which combine hydrophobic and hydrophilic segments. The polymers adsorb strongly on the fabric, are easily dispersed or dissolved in a surfactant and are compatible with the components of the detergent formulation.

15 When incorporated in a detergent formulation, they aid oily soil removal.

Various soil release polymers have been disclosed in the prior art for removal of oily soils from polyester. A vast

20 majority are polyesters that have been hydrophilically modified. US3959230 and US4116885 disclose modified polyesters as soil release agents for detergent formulations.

EP185427 discloses further anionic modification of

25 hydrophilically modified polyesters. This is said to increase hydrophilicity and improve water solubility of the SRP. The polymers aid the removal of oily soil from polyester fabrics.

GB2322137 discloses the hydrophobic modification of starch

30 (starch is the hydrophilic segment) and its use as a soil release polymer, in particular for detergency of oily soil

from polyester fabric. Hydrophobic modification was carried out by graft copolymerising starch with hydrophobic monomers.

5 SRPs for removal of oily soil from cotton have also been disclosed. US3948838 discloses the use of copolymers of hydrophobic acrylic monomers and water soluble monomers like acrylic acid, as oily soil release agents for cotton fabrics.

10 Hence, polymers are known in the prior art for removal of oily soil from cotton or polyester. However, polymers that can aid removal of oily and particulate soil or their mixtures from cotton and polyester have not been disclosed.

15


SUMMARY OF THE INVENTION

Thus according to the present invention, novel soil release polymers that are anionic, hydrophobic graft copolymers of
20 polysaccharides are provided. The soil release polymers can be incorporated in detergent formulations and aid the removal of oily and particulate soil from cotton, polyester or their blends. The polymers can also be used in rinse conditioners. A process for making these soil release
25 polymers comprising the steps of anionic modification and graft copolymerisation is also provided.

DEFINITION OF THE INVENTION

According to a first aspect of the present invention, there is provided an anionic, hydrophobic polysaccharide which is a graft copolymer of a polysaccharide having anionic substituents with an ethylenically unsaturated monomer, the copolymer having a polysaccharide backbone carrying grafted hydrophobic vinyl polymeric groups derived from the ethylenically unsaturated monomer, and anionic substituents, preferably selected from carboxylate and sulphonate groups.

More specifically the invention provides an anionic, hydrophobic polysaccharide having the general formula I:



wherein R is a hydrophobic vinyl polymer, R' and R'' which may or may not be the same represents a carboxylic acid or a sulphonic acid group or its salt and G is a monosaccharide or substituted monosaccharide.

According to a second aspect of the present invention there is provided a process for the preparation of an anionic, hydrophobic polysaccharide as previously defined, comprising the steps of graft copolymerisation and anionic modification of a polysaccharide.

According to a third aspect of the present invention there is provided a fabric treatment composition comprising a fabric treatment agent and from 0.01 to 10 wt% of a anionic, hydrophobic polysaccharide as previously defined.

5

According to a fourth aspect of the present invention there is provided a detergent composition comprising from 5 to 60 wt% of a deterative surfactant and from 0.01 to 10 wt% of an anionic, hydrophobic polysaccharide as previously

10 defined.


DETAILED DESCRIPTION OF THE INVENTION

15

The anionic, hydrophobic polysaccharide

The anionic, hydrophobic graft copolymer of polysaccharide of the current invention has the general structure given below:

20



25

wherein R is a hydrophobic vinyl polymer, R' and R'' which may or may not be the same, represent a carboxylic or a sulphonic acid group or its salt and G is a monosaccharide or substituted monosaccharide.

30

It is preferable that G is a monosaccharide.

The hydrophobic polymer can be attached to the polysaccharide backbone through the hydroxyl group or through any of the carbon atoms on the sugar. The polymer chains can be present at irregular intervals on the polysaccharide chain and it is not critical that they be present at regular intervals. Up to 50% homopolymer may be present without impairing soil release performance. The anionic group is attached to the polysaccharide backbone through the hydroxyl group, either primary or secondary. It is not essential that anionic substituents be present on each of the sugar rings.

It is not essential to remove any unreacted polysaccharide that may be present in the final product obtained by graft copolymerisation and anionic modification of the polysaccharide.

The polysaccharide, which is the hydrophilic part of the molecule, is preferably chosen from cellulose, guar gum, starch and tamarind kernel powder but is not limited by the same. More preferably the polysaccharide is starch. The starch can be any native starch and includes those derived from wheat, rice, oat, tapioca, maize, potato, sorghum, arrowroot or their mixtures thereof. Alternatively, acid or enzymatically degraded starch or oxidised starch or their mixtures or their mixtures thereof with the native starches can also be used.

When starch is the preferred polysaccharide, it may be in the native form or gelatinised form. The term gelatinisation refers to rupture of the starch granule at elevated temperatures in presence of water.


5

The hydrophobic modification is provided by a hydrophobic polymer (R in Formula I) grafted onto the polysaccharide backbone. The polymers of vinyl monomers like acrylic monomers, vinyl acetate, styrene and substituted styrenes are especially preferred. The molecular weight of each of the hydrophobic polymer chains is preferably 500-5,000,000, more preferably from 2000-500,000 and most preferably from 5000-100,000.

15 The amount of the hydrophobic polymer is preferably 0.1-10% by weight of the polysaccharide, more preferably from 1-5% by weight of the polysaccharide.

Preferably, acrylic monomers are used for graft
20 copolymerisation. The hydrophobic acrylic polymers especially suitable for the present invention are shown below.

25



30 wherein R_1 and R_1' may or may not be the same and represent -
H, $-\text{CH}_3$, $-\text{C}_2\text{H}_5$.

and wherein R_2 and R_2' may or may not be the same and represent $-\text{COOCH}_3$, $-\text{COOC}_2\text{H}_5$, $-\text{COOC}_3\text{H}_7$.

Particularly preferred is poly (methyl acrylate) wherein $R_1 =$
5 $R_1' = \text{H}$ and $R_2 = R_2' = -\text{COOCH}_3$.

The anionic group, which is a carboxylic acid or a sulphonic acid group or its salt, is distributed along the backbone of the polysaccharide. The compounds of the invention may
10 contain both carboxylic acid and sulphonic acid groups (or their salts) as anionic substituents.

The amount of the anionic substituent is preferably 0.1-10% by weight of the polysaccharide, more preferably from 0.1-5%
15 by weight of the polysaccharide.


Preferred examples of anionic reactants are halocarboxylic acids or their salts and vinyl sulphonic acid or their salts or their mixtures thereof. More preferably the
20 halocarboxylic acids are used as anionic reagents. Chloroacetic acid is especially preferred.

Description of the drawings

25

The accompanying drawings show representative examples of e anionic, hydrophobic polysaccharides of the invention.

In the drawings,



10

$R_1 = H$ and $R_2 = -COOCH_3$

and $R' = -CH_2COOH$.

15 Figure 1a represents an anionic, hydrophobic graft copolymer of starch.

Figure 1b represents an anionic, hydrophobic graft copolymer of cellulose.

20

Figure 1c represents an anionic, hydrophobic graft copolymer of guar gum.

Figure 1d represents an anionic, hydrophobic graft copolymer of tamarind gum.

25

Figure 2a represents the anionic modification of starch.

Figure 2b represents the anionic modification of cellulose.

30

Figure 2c represents the anionic modification of guar gum.

Figure 2d represents the anionic modification of tamarind gum.

Figure 3a represents a hydrophobic graft copolymer of
5 starch.

Figure 3b represents a hydrophobic graft copolymer of cellulose.

10 Figure 3c represents a hydrophobic graft copolymer of guar gum.

Figure 3d represents a hydrophobic graft copolymer of
15 tamarind gum.

Preparation of the anionic, hydrophobic polysaccharides

20 The soil release polymers of the invention are prepared by a) graft copolymerisation and b) anionic modification of the polysaccharide. It is not particularly relevant for the present invention as to which step is carried out first. Preferably, the step of graft copolymerisation of the
25 polysaccharide is carried out first, followed by anionic modification.

Both graft copolymerisation and anionic modification of the polysaccharide can take place through the primary and/or the
30 secondary hydroxyl groups on the polysaccharide backbone.

Graft copolymerisation can also be initiated by H abstraction from the monosaccharide residue.

Graft copolymerisation is carried out by contacting the redox
5 initiator, such as ferrous ammonium sulphate and hydrogen peroxide or ceric ammonium nitrate and dilute nitric acid, with the polysaccharide in an aqueous medium. A preferred temperature range is 20-60°C., more preferably from 30-40 °C. It is preferable to add an entrainer, an example of which is
10 urea. When the ferrous ammonium sulphate and hydrogen peroxide system is used as the redox initiator, it is preferable to also add ascorbic acid. The hydrophobic monomer is added and subsequent polymerisation takes place to yield the polymer of the invention.

15

The hydrophobic graft copolymer so prepared is preferably reacted with a carboxylating or sulphonating reagent selected from halocarboxylic acid, an alkali or alkaline earth metal salt of a halocarboxylic acid, vinyl sulphonic
20 acid or the alkali or alkaline earth metal salt of the vinyl sulphonic acid. It is preferable to use haloacetic acid, more preferably chloroacetic acid, to provide anionic groups on the polysaccharide. The process of anionic modification may be carried out in presence of a solvent such as
25 water/isopropanol mixtures or as a dry process.

When the soil release polymer of the invention is prepared from native starch, it is preferred to subject the same to a temperature of 70-90°C in presence of water, to make the soil
30 release polymer water soluble.

Fabric treatment and detergent compositions

5 The soil release polymer of the invention may be used to treat fabric by incorporating it into detergent compositions, rinse conditioners or other fabric treatment compositions. It can also be used simply as an aqueous solution which can be applied to the fabric to enhance soil removal from the fabric.

10

The polymers of the invention are suitably incorporated at the level of 0.01-10 wt%, preferably 0.5-5 wt%, of the detergent or fabric treatment composition.

15 The soil release polymers may advantageously be incorporated into built laundry detergent compositions suitable for heavy duty use. A preferred detergent composition in accordance with the invention may contain from 5 to 40 wt% of deterative surfactant (detergent-active material), from 5 to 80 wt% of
20 detergency builder, and from 0.01 to 10 wt%, preferably from 0.5 to 5 wt%, of the soil release polymer of the invention.

Apart from the polymers of the invention, the detergent formulations also contain as in conventional formulations,
25 detergent actives (surfactants) and builders and auxiliaries. Auxiliaries include sequestrants, dye-transfer inhibitors, perfumes, bleaches, enzymes, flourescers, optical brighteners, fungicides, germicides, hydrotropes etc.

30 The detergent composition may be in any physical form, for example, powder, tablet, bar, paste or liquid.

The detergent active material is generally chosen from anionic, nonionic, cationic, zwitterionic detergent active compounds and mixtures thereof.

- 5 Anionic surfactants which can be used in the compositions of the invention are both soap and non-soap detergents compounds. Especially suitable anionic detergent active compounds are water soluble salts of organic sulphuric reaction products having in the molecular structure an alkyl
10 radical containing from 8 to 22 carbon atoms, and a radical chosen from sulphonic acid or sulphur acid ester radicals and mixtures thereof.

- The preferred water-soluble synthetic anionic detergent
15 active compounds are the alkali metal (such as sodium and potassium) and alkaline earth metal (such as calcium and magnesium) salts of higher alkyl benzene sulphonates and mixtures with olefin sulphonates and higher alkyl sulphates, and the higher fatty acid monoglyceride sulphates. The most
20 preferred anionic detergent active compounds are higher alkyl aromatic sulphonates such as higher alkyl benzene sulphonates containing from 6 to 20 carbon atoms in the alkyl group in a straight or branched chain, particular examples of which are sodium salts of higher alkyl benzene
25 sulphonates or of higher-alkyl toluene, xylene or phenol sulphonates, alkyl naphthalene sulphonates, ammonium diamyl naphthalene sulphonate, and sodium dinonyl naphthalene sulphonate.
- 30 Suitable nonionic detergent active compounds can be broadly described as compounds produced by the condensation of

alkylene oxide groups, which are hydrophilic in nature, with an organic hydrophobic compound which may be aliphatic or alkyl aromatic in nature. The length of the hydrophilic or polyoxyalkylene radical which is condensed with any particular hydrophobic group can be readily adjusted to yield a water-soluble compound having the desired degree of balance between hydrophilic and hydrophobic elements.

Particular examples include the condensation product of aliphatic alcohols having from 8 to 22 carbon atoms in either straight or branched chain configuration with ethylene oxide, such as a coconut oil ethylene oxide condensate having from 2 to 15 moles of ethylene oxide per mole of coconut alcohol; condensates of alkylphenols whose alkyl group contains from 6 to 12 carbon atoms with 5 to 25 moles of ethylene oxide per mole of alkylphenol; condensates of the reaction product of ethylenediamine and propylene oxide with ethylene oxide, the condensate containing from 40 to 80% of polyoxyethylene radicals by weight and having a molecular weight of from 5,000 to 11,000; tertiary amine oxides of structure R_3NO , where one group R is an alkyl group of 8 to 18 carbon atoms and the others are each methyl, ethyl or hydroxyethyl groups, for instance dimethyldodecylamine oxide; tertiary phosphine oxides of structure R_3PO , where one group R is an alkyl group of from 10 to 18 carbon atoms, and the others are each alkyl or hydroxyalkyl groups of 1 to 3 carbon atoms, for instance dimethyldodecylphosphine oxide; and dialkyl sulphoxides of structure R_2SO where the group R is an alkyl group of from 10 to 18 carbon atoms and the other is methyl or ethyl, for instance methyltetradecyl sulphoxide; fatty acid

alkylolamides; alkylene oxide condensates of fatty acid
alkylolamides and alkyl mercaptans.

- Suitable amphoteric detergent-active compounds that
5 optionally can be employed are derivatives of aliphatic
secondary and tertiary amines containing an alkyl group of 8
to 18 carbon atoms and an aliphatic radical substituted by
an anionic water-solubilizing group, for instance sodium 3-
dodecylamino-propionate, sodium 3-dodecylaminopropane
10 sulphonate and sodium N-2-hydroxydodecyl-N-methyltaurate.
Suitable cationic detergent-active compounds are quaternary
ammonium salts having an aliphatic radical of from 8 to 18
carbon atoms, for instance cetyltrimethyl ammonium bromide.
- 15 Suitable zwitterionic detergent-active compounds that
optionally can be employed are derivatives of aliphatic
quaternary ammonium, sulphonium and phosphonium compounds
having an aliphatic radical of from 8 to 18 carbon atoms and
an aliphatic radical substituted by an anionic water-
20 solubilising group, for instance 3-(N-N-dimethyl-N-
hexadecylammonium), propane-1-sulphonate betaine, 3-
(dodecylmethyl sulphonium) propane-1-sulphonate betaine and
3-(cetylmethylphosphonium) ethane sulphonate betaine.
- 25 Further examples of suitable detergent-active compounds are
compounds commonly used as surface-active agents given in
the well-known textbooks "Surface Active Agents", Volume I
by Schwartz and Perry and "Surface Active Agents and
Detergents", Volume II by Schwartz, Perry and Berch.

The detergency builders used in the formulation are preferably inorganic and suitable builders include alkali metal aluminosilicates (zeolites), alkali metal carbonate, sodium tripolyphosphate (STPP), tetrasodium pyrophosphate (TSPP), citrates, sodium nitrilotriacetate (NTA) and combinations of these. Builders may suitably be used in amounts ranging from 5 to 80 wt%, preferably from 10 to 60 wt%.

10 The detergent compositions of the invention may also contain any other suitable ingredients. These may be selected from, but are not limited to, bleaches, bleach precursors, bleach stabilisers (heavy metal sequestrants), photobleaches, enzymes, other polymers, foam boosters, foam controllers, 15 fluorescers, fillers, flow aids, fabric conditioning agents, perfumes, colourants, and coloured speckles.

The polymers of the invention may also be used as part of a fabric washing kit, as part of a sachet or can be 20 microencapsulated.

A fabric washing kit may comprise two enclosures separated from each other. It is preferred that one enclosure is big and the other small. The big enclosure contains the detergent 25 formulation and the small enclosure the polymer. An instruction sheet contains directions for the use of the two components including the proportions and conditions under which these are to be used. The kit may also contain a dispensing means to aid the washing using the two components 30 in the desired proportions.

- 17 -

A preferred kit according to the invention is a plastic container having two separate chambers. A first bigger chamber holds the detergent composition. The second small chamber has a volume capacity not greater than about 10% of the big chamber and holds the soil release polymer of the invention.

The polymer/detergent composition may also be packaged in single dose sachet having a compartment in which the two components are housed in a manner such that they come into contact when the contents are discharged from the sachet. It is also possible to microencapsulate the polymer and provide the product in a premixed form. Other forms of packagings are also included within the scope of invention.

15

The invention is illustrated further by the following non-limiting examples, in which parts and percentages are by weight unless otherwise stated.

EXAMPLESExample 1Synthesis of soil release polymer

5

100 g urea was dissolved in 1 litre of distilled water in a flask equipped with a stirrer and a thermometer. 1 kg of tapioca starch , 1 g ferrous ammonium sulphate and 5 g ascorbic acid, 50 ml. methyl acrylate were added

10 sequentially and the mixture was stirred. 10 ml hydrogen peroxide (30% w/v) was then added, the reaction mixture stirred and then filtered. The reaction was conducted at 30°C. The starch-graft-poly (methyl acrylate) obtained was repeatedly washed with water and then dried at 100°C.

15

250 g of chloroacetic acid and 240 g of sodium hydroxide was dissolved in water and mixed under stirring maintaining a temperature of <20°C. 40 g urea was then added to the mixture. 1 kg of the above starch-graft-poly (methyl

20 acrylate) was taken in a mixer and the chloroacetic acid-sodium hydroxide mixture was then sprayed on to the same under stirring. The mixture was left for 24 hours at 60°C and then dried to 11% moisture.

25

Example 2Demonstration of soil removal properties of the polymer

A standard detergent formulation without a soil release
5 polymer was formulated (Comparative Example A). A detergent
formulation incorporating the polymer of Example 1 was also
prepared. The formulation details are presented in Table 1.

Table 1

Composition % wt.	Comparative Example A	Example 1
Linear alkyl benzene sulphonate	20	20
Sodium tripolyphosphate	27	27
Soda	15	15
Alkaline silicate	10	10
Fillers	15	15
Soil Release Polymer	-	2
Water	To 100	To 100

10

Soil release is determined by improvement in detergency.

100% cotton and 100% polyester fabric were used in the
study. The fabric was cut into swatches of dimension 5" X
15 5". The swatches were soiled using a) oily soil and b)
particulate soil (carbon soot). The oily soil could be
sebum prepared in the lab or motor oil. A red dye at a
concentration of 0.025% is added to the oil to clearly
determine oil removal from the fabric.

- 20 -

Commercially available fabrics presoiled with a mixture of oily and particulate soil (WFK 30D was pre-soiled polyester and WFK 10D was pre-soiled cotton) were also used.

5 0.2g of soil along with oil red dye at a concentration of 0.025% was loaded on to each of the test swatches and the stain was allowed to wick for a period of 24 hrs. Initial reflectance measurement at 520 nm was taken, on a Milton Roy Color Scan II. 520 nm is the wavelength at which the red
10 dye absorbs, hence it is used to monitor soil removal.

For particulate soil loading, carbon soot was deposited to the cloth piece to get a reflectance of 55. The reflectance was determined at 460 nm.

15

The fabrics mentioned above were washed using the detergent compositions of Comparative Example A and Example 1, maintaining 10 replicates for each. Detergent solutions of concentration 5g/l were then prepared.

20

Test swatches were washed in a tergotometer in the detergent solution for a period of 15 minutes. Reflectance measurements were taken at 520nm (for oily soil) or 460 nm (for particulate soil and WFK 10D and 30D). The difference in
25 reflectance of the soiled fabrics before and after washing was noted and represented as ΔR_{520^*} or ΔR_{460^*} .

The improvement in soil removal for oily soil was determined as follows:

30

Improvement in oily soil removal ($\Delta\Delta R520^*$) = $\Delta R520^*$ (for Example 1) - $\Delta R520^*$ (for Comparative Example A).

The improvement in soil removal for particulate and mixtures
5 of oily and particulate was determined as follows:

Improvement in soil removal ($\Delta\Delta R460^*$) = $\Delta R460^*$ (for Example 1)
- $\Delta R460^*$ (for Comparative Example A)

10 The results of the tergotometer washes following the above
detergency test procedure for removal of soils from polyester
are presented in Table 2. Test results for cotton are
presented in Table 3.

15 Table 2 - polyester

Particulate soil	$\Delta\Delta R460^*$	2.4
Artificial sebum	$\Delta\Delta R520^*$	1.6
Motor oil	$\Delta\Delta R520^*$	2.5
Mixture of oily and particulate soil	$\Delta\Delta R460^*$	2.0

Table 3 - cotton

20

Particulate soil	$\Delta\Delta R460^*$	3.0
Artificial sebum	$\Delta\Delta R520^*$	0.5
Motor oil	$\Delta\Delta R520^*$	0.5
Mixture of oily and particulate soil	$\Delta\Delta R460^*$	2.0

- 22 -

The above reflectance measurements indicate benefits in use of an anionic, hydrophobic graft copolymer of starch in removal of both oily and particulate soil or their mixture on both polyester and cotton fabric.

CLAIMS

1 Anionic, hydrophobic polysaccharide which is a graft
5 copolymer of a polysaccharide having anionic substituents
 with an ethylenically unsaturated monomer, the copolymer
 having a polysaccharide backbone carrying grafted
 hydrophobic vinyl polymeric groups derived from the
 ethylenically unsaturated monomer, and anionic substituents.


10

2 Anionic, hydrophobic polysaccharide according to claim
1, wherein the anionic substituents are selected from
carboxylate and sulphonate groups.

15

3 Anionic, hydrophobic polysaccharide having the general
formula I:

20



25

wherein R is a hydrophobic vinyl polymer, R' and R'' which may
or may not be the same represents a carboxylic acid or a
30 sulphonic acid group or its salt and G is a monosaccharide
 or substituted monosaccharide.

4 Anionic, hydrophobic polysaccharide according to claim 3, wherein R' and R" are selected from $-R_3-COOH$, $-R_3-COO^-M^+$, $-(CH_2-CHSO_3H)_n$, $-(CH_2-CH-SO_3^-M^+)_n$, wherein R_3 is an alkyl group (C_1-C_4) and M is an alkali or alkaline earth metal.

5

5 Anionic, hydrophobic polysaccharide according to claim 4, wherein $R' = R'' = -CH_2-COOH$ or its metal salt.

10

6 Anionic, hydrophobic polysaccharide according to any preceding claim, wherein the amount of the hydrophobic vinyl polymer is 0.1-10% by weight of the polysaccharide.

15

7 Anionic, hydrophobic polysaccharides according to claim 6, wherein the amount of the hydrophobic vinyl polymer is 1-5% by weight of the polysaccharide.

20

8 Anionic, hydrophobic polysaccharide according to any preceding claim, wherein the amount of anionic substituent is 0.1-10% by weight of the polysaccharide.

25

9 Anionic, hydrophobic polysaccharide according to claim 8, wherein the amount of anionic substituent is 0.1-5% by weight of the polysaccharide.

30

10 Anionic, hydrophobic polysaccharide according to any preceding claim, wherein the hydrophobic polymer has a molecular weight from 500 to 5,000,000.

5

11 Anionic, hydrophobic polysaccharide according to claim 8, wherein the hydrophobic polymer has a molecular weight from 2000 to 500,000.


10

12 Anionic, hydrophobic polysaccharide according to claim 11, wherein the hydrophobic polymer has a molecular weight from 5000 to 100,000.

15

13 Anionic, hydrophobic polysaccharide according to any preceding claim, wherein R is an acrylic polymer, having the general formula II

20



25

wherein R_1 and R_1' may or may not be the same and represent -
H, $-\text{CH}_3$, $-\text{C}_2\text{H}_5$.

30

and wherein R_2 and R_2' may or may not be the same and represent $-\text{COOCH}_3$, $-\text{COOC}_2\text{H}_5$, $-\text{COOC}_3\text{H}_7$.

14 Anionic, hydrophobic polysaccharide according to claim 13, wherein $R_1 = R_1' = H$ and $R_2 = R_2' = -COOCH_3$.

5 15 Anionic, hydrophobic polysaccharide according to any preceding claim, wherein the polysaccharide is selected from starch, modified starches, cellulose, guar gum, and tamarind gum.

10

16 Anionic, hydrophobic polysaccharide according to claim 15, wherein the polysaccharide is starch..

15 17 A process for the preparation of an anionic, hydrophobic polysaccharide according to any one of claims 1 to 16, comprising graft copolymerisation and anionic modification of a polysaccharide.

20

18 A process according to claim 17, comprising graft copolymerisation of the polysaccharide or the anionically modified polysaccharide using a redox initiator.

25

19 A process according to claim 18, comprising graft copolymerisation of the polysaccharide or the anionically modified polysaccharide using ferrous ammonium sulphate and hydrogen peroxide as the redox initiator.

30

20 A process according to any one of claims 17 to 19,
comprising anionic modification of the polysaccharide or the
graft copolymerised polysaccharide using halocarboxylic acid
or its salt or vinyl sulphonic acid or its salt or their
5 mixtures thereof.

21 A process according to claim 20, comprising anionic
modification of the polysaccharide or the graft
10 copolymerised polysaccharide using halocarboxylic acid or
its salt.

22 A process according to claim 21, wherein the
15 halocarboxylic acid or salt is chloroacetic acid or its
salt.

23 A fabric treatment composition comprising a fabric
20 treatment agent and from 0.01 to 10 wt% of an anionic,
hydrophobic polysaccharide according to any one of claims 1
to 16.

24 A detergent composition comprising from 5 to 60 wt% of
25 a deterative surfactant and from 0.01 to 10 wt% of an
anionic, hydrophobic polysaccharide according to any one of
claims 1 to 16.

25 A detergent composition according to claim 24, which is
a built laundry detergent composition comprising from 5 to
40 wt% of deterative surfactant, from 5 to 80 wt% of
detergency builder, and from 0.01 to 10 wt% of an anionic,
5 hydrophobic polysaccharide according to any one of claims 1
to 16.

26 A detergent compositions according to claim 24 or
10 claim 25, which comprises from 0.5 to 5 wt% of the anionic,
hydrophobic polysaccharide according to any one of claims 1
to 16.

15

*


*

*

- 29 -


ABSTRACT

Anionic, hydrophobic polysaccharides useful as soil release agents in detergent compositions are graft copolymers of a polysaccharide having anionic substituents with an ethylenically unsaturated monomer, the copolymer having a polysaccharide backbone carrying grafted hydrophobic vinyl polymeric groups derived from the ethylenically unsaturated monomer, and anionic substituents. The polymers exhibit enhanced release of both oily and particulate soil from both polyester and cotton.




FORMULA II

FIG. 1a : ANIONIC HYDROPHOBIC GRAFT COPOLYMER OF STARCH




FORMULA II

FIG. 1b : ANIONIC HYDROPHOBIC GRAFT COPOLYMER OF CELLULOSE.




FORUMLA II

FIG. 1c : ANIONIC HYDROPHOBIC GRAFT COPOLYMER OF GUAR GUM.




Where X =



XYLOSE

G =



GALACTOSE

FORUMLA II

FIG. 1d : ANIONIC HYDROPHOBIC GRAFT COPOLYMER OF TAMARIND GUM.




FIG. 2 a : ANIONIC MODIFICATION OF STARCH.




FIG. 2 b : ANIONIC MODIFICATION OF CELLULOSE






FIG. 2 c : ANIONIC MODIFICATION OF GUAR GUM.



Where X =



G =




FIG. 2 d : ANIONIC MODIFICATION OF TAMARIND GUM.





FIG. 3a : HYDROPHOBIC GRAFT COPOLYMER OF STARCH



CELLULOSE
FIG. 3b : HYDROPHOBIC GRAFT COPOLYMER OF ~~STARCH~~




FIG. 3 c : HYDROPHOBIC GRAFT COPOLYMER OF GUAR GUM.




FIG. 3 d : HYDROPHOBIC GRAFT COPOLYMER OF TAMARIND GUM.